

23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai - 400 701, INDIA.

Phone: +91 93244 69890 Email: lab@gvmtesthouse.com www.gvmtesthouse.com



TESTING T

TRAINING

AUDITING

Test Order Ref: GVM/COATING/04840-3-1/02/2024

Date of Receipt:09.02.2024

Date: 26.02.2024

Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village - Vasind, Taluka - Shahapur, Vasind,

Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample

Sample Supplied by the Customer

No. of Product tested

01 (One Only)

Customer's Reference

PO No. VSND/2010014020/SER/R/2620008695, dt. -12.02.2024

Condition of Sample

Satisfactory

Date of Receipt

09.02.2024

Lab Reference Number Sample Identification # 2024/FEB/04840-3-1 Nippon Paint Satin Glo+

Period of Test

12.02.2024 to 26.02.2024

Test Method #

ASTM D 4828-1994

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	7
3	Теа	100	5
4	Coffee	100	5
5	Highlighter	100	7
6	Crayon	100	10
7	Tomato Ketchup	100	7
8	Lipstick	100	5
9	Mud	100	10
10	Turmeric	100	5

Rating Scala as per ASTM D 4828

- 0 No change from original intensity (depth) of stain
- 3- Slight change from original, but readily visible
- 5- Moderate change from original, slightly visible, and
- 7- Large change from original, barely visible
- 10 All Stain removed

As furnished by the customer.

Note:

- 1. The results relate only to the items tested.
- 2. Report shall not be reproduced except in full, without the written approval of lab.
- 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE







402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA. GSTIN: 27BPBPB4090Q1ZM



23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai - 400 701, INDIA. Phone: +91 93244 69890 Email: lab@gvmtesthouse.com

www.gvmtesthouse.com



ISO 9001:2015 Certified

TESTING

TRAINING

AUDITING

Test Order Ref: GVM/COATING/04673-3-2/01/2024

Date of Receipt: 09.02.2024

Date: 26.02.2024 Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village - Vasind, Taluka - Shahapur, Vasind, Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample

Sample Supplied by the Customer

No. of Product tested

01 (One Only)

Customer's Reference

PO No. VSND/2010014020/SER/R/2620008695, dt. -12.02.2024

Condition of Sample

Satisfactory

Date of Receipt Lab Reference Number 09.02.2024 2024/FEB/04840-3-2

Sample Identification #

Nippon Paint Spotless nxt 12.02.2024 to 26.02.2024

Period of Test Test Method #

ASTM D 4828-1994

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	7
3	Tea	100	5
4	Coffee	100	5
5	Highlighter	100	7
6	Crayon	100	10
7	Tomato Ketchup	100	7
8	Lipstick	100	5
9	Mud	100	10
10	Turmeric	100	5

Rating Scala as per ASTM D 4828

- 0 No change from original intensity (depth) of stain
- 3- Slight change from original, but readily visible
- 5- Moderate change from original, slightly visible, and
- 7- Large change from original, barely visible
- 10 All Stain removed
- # As furnished by the customer.

- 1. The results relate only to the items tested.
- 2. Report shall not be reproduced except in full, without the written approval of lab.
- 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE





402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA. GSTIN: 27BPBPB4090Q1ZM



23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai - 400 701, INDIA.

Phone: +91 93244 69890 Email: lab@gvmtesthouse.com www.gvmtesthouse.com



TESTING

TRAINING

AUDITING

Test Order Ref: GVM/COATING/04673-3-3/01/2024

Date of Receipt:09.02.2024

Date: 26.02.2024

Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village – Vasind, Taluka – Shahapur, Vasind,

Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample

Sample Supplied by the Customer

No. of Product tested

01 (One Only)

Customer's Reference

PO No. VSND/2010014020/SER/R/2620008695, dt. -12.02.2024

Condition of Sample :

Satisfactory

Date of Receipt

09.02.2024

Lab Reference Number

2024/FEB/04840-3-3

Sample Identification # : Period of Test :

Nerolac Impressions Ultra HD 12.02.2024 to 26.02.2024

Test Method #

ASTM D 4828-1994

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	10
3	Tea	100	7
4	Coffee	100	7
5	Highlighter	100	10
6	Crayon	100	10
7	Tomato Ketchup	100	7
8	Lipstick	100	7
9	Mud	100	10
10	Turmeric	100	7

Rating Scala as per ASTM D 4828

- 0 No change from original intensity (depth) of stain
- 3- Slight change from original, but readily visible
- 5- Moderate change from original, slightly visible, and
- 7- Large change from original, barely visible
- 10 All Stain removed
- # As furnished by the customer.

Note:

- 1. The results relate only to the items tested.
- 2. Report shall not be reproduced except in full, without the written approval of lab.
- 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE







402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA. GSTIN: 27BPBPB4090Q1ZM