

23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node,

Navi Mumbai - 400 701, INDIA. Phone: +91 93244 69890

Email: lab@gvmtesthouse.com www.gvmtesthouse.com



TESTING

TRAINING

AUDITING

Test Order Ref: GVM/COATING/03564-1-2/04/2023

ULR: TC906123000001639F

Date: 20.07.2023 Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village - Vasind, Taluka - Shahapur, Vasind, Thane, Maharashtra -421604

TEST REPORT ON HALO MAJESTIC INTERIORS SHINE

Source of Sample

Sample Supplied by the Customer

No. of Product tested

01 (One Only)

Customer's Reference

PO No. VSND/2010014020/SER/R/2620007218, dt. -20.06.2023

Condition of Sample

Satisfactory

Date of Receipt

23.06.2023

Lab Reference Number

2023/JUN/03564-1-2

Sample Identification #

Halo Majestic Interiors Shine

Application Details #

Applied 2 coats of Halo Majestic Interiors Shine with 25% dilution with

coverage of 110 sqft/L

Curing Condition #

14 days @ 23 ± 2 °C & 65±5% RH

Period of Test

05.07.2023 to 20.07.2023

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Crack Bridging Ability	mm	0.59	EN 1062-7(A): 2004

As furnished by the customer.

- 1. The results relate only to the items tested.
- 2. Report shall not be reproduced except in full, without the written approval of lab.
- 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE



