



23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



TC-9061

GVM TEST HOUSE
AND RESEARCH CENTRE

TESTING | TRAINING | AUDITING

Test Order Ref: GVM/COATING/04673-1-1/01/2024
ULR: TC90612400000224F

Date: 07.02.2024
Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED
Vasind Village – Vasind,
Taluka – Shahapur, Vasind,
Thane, Maharashtra -421604

TEST REPORT ON DULUX VELVET TOUCH PEARL GLO

Source of Sample : Sample Supplied by the Customer
No. of Product tested : 01 (One Only)
Customer's Reference : PO No. VSND/2010014020/SER/R/2620008355, dt. -11.01.2024
Condition of Sample : Satisfactory
Date of Receipt : 17.01.2024
Lab Reference Number : 2024/JAN/04673-1-1
Sample Identification # : Dulux Velvet Touch Pearl Glo
Application Details # : Applied 2 coats of Dulux VT Pearl Glo with 35% dilution with coverage of 110 sqft/L
Curing Condition # : 14 days @ 23 ± 2 °C & 65±5% RH
Period of Test : 19.01.2024 to 05.02.2024

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Crack Bridging Ability	mm	0.22	EN 1062-7(A): 2004

As furnished by the customer.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of lab.
 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE



DINESH BURDE

Dinesh Burde

Authorised Signatory



Regd. Office:

402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.
GSTIN: 27BPBPB4090Q1ZM



ISO 9001:2015 Certified



23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



TC-9061

GVM TEST HOUSE
AND RESEARCH CENTRE

TESTING | TRAINING | AUDITING

Test Order Ref: GVM/COATING/04673-1-2/01/2024
ULR: TC906124000000225F

Date: 07.02.2024
Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED
Vasind Village – Vasind,
Taluka – Shahapur, Vasind,
Thane, Maharashtra -421604

TEST REPORT ON DULUX VELVET TOUCH DIAMOND GLO

Source of Sample : Sample Supplied by the Customer
No. of Product tested : 01 (One Only)
Customer's Reference : PO No. VSND/2010014020/SER/R/2620008355, dt. -11.01.2024
Condition of Sample : Satisfactory
Date of Receipt : 17.01.2024
Lab Reference Number : 2024/JAN/04673-1-2
Sample Identification # : Dulux Velvet Touch Diamond Glo
Application Details # : Applied 2 coats of Dulux Velvet Touch Diamond Glo with 35% dilution with coverage of 110 sqft/L
Curing Condition # : 14 days @ 23 ± 2 °C & 65±5% RH
Period of Test : 19.01.2024 to 05.02.2024

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Crack Bridging Ability	mm	0.21	EN 1062-7(A): 2004

As furnished by the customer.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of lab.
 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE



DINESH BÜRDE
[Signature]
Authorised Signatory



Regd. Office:
402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.
GSTIN: 27BPBPB4090Q1ZM



ISO 9001:2015 Certified



23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



TC-9061

GVM TEST HOUSE
AND RESEARCH CENTRE

TESTING | TRAINING | AUDITING

Test Order Ref: GVM/COATING/04673-1-3/01/2024
ULR: TC906124000000226F

Date: 07.02.2024
Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED
Vasind Village – Vasind,
Taluka – Shahapur, Vasind,
Thane, Maharashtra -421604

TEST REPORT ON NEROLAC IMPRESSIONS HD PREMIUM LUXURY EMULSION

Source of Sample : Sample Supplied by the Customer
No. of Product tested : 01 (One Only)
Customer's Reference : PO No. VSND/2010014020/SER/R/2620008355, dt. -11.01.2024
Condition of Sample : Satisfactory
Date of Receipt : 17.01.2024
Lab Reference Number : 2024/JAN/04673-1-3
Sample Identification # : Nerolac Impressions HD Premium Luxury Emulsion
Application Details # : Applied 2 coats of Nerolac Impressions HD Premium Luxury Emulsion
with 45% dilution
with coverage of 110 sqft/L
Curing Condition # : 14 days @ 23 ± 2 °C & 65±5% RH
Period of Test : 19.01.2024 to 05.02.2024

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Crack Bridging Ability	mm	0.29	EN 1062-7(A): 2004


As furnished by the customer.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of lab.
 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE



DINESH BURDE
[Signature]
Authorised Signatory



Regd. Office:
402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.
GSTIN: 27BPBPB4090Q1ZM



ISO 9001:2015 Certified



23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



TC-9061

GVM TEST HOUSE
AND RESEARCH CENTRE

TESTING | TRAINING | AUDITING

Test Order Ref: GVM/COATING/04673-1-4/01/2024
ULR: TC906124000000227F

Date: 07.02.2024
Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED
Vasind Village – Vasind,
Taluka – Shahapur, Vasind,
Thane, Maharashtra -421604

TEST REPORT ON NEROLAC IMPRESSIONS KASHMIR LUXURY EMULSION

Source of Sample : Sample Supplied by the Customer
No. of Product tested : 01 (One Only)
Customer's Reference : PO No. VSND/2010014020/SER/R/2620008355, dt. -11.01.2024
Condition of Sample : Satisfactory
Date of Receipt : 17.01.2024
Lab Reference Number : 2024/JAN/04673-1-4
Sample Identification # : Nerolac Impressions Kashmir Luxury Emulsion
Application Details # : Applied 2 coats of Nerolac Impressions Kashmir Luxury Emulsion
with 45% dilution
with coverage of 110 sqft/L
Curing Condition # : 14 days @ 23 ± 2 °C & 65±5% RH
Period of Test : 19.01.2024 to 05.02.2024

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Crack Bridging Ability	mm	0.33	EN 1062-7(A): 2004

As furnished by the customer.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of lab.
 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE



DINESH BURDE

(Signature)
Authorised Signatory



Regd. Office:

402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.
GSTIN: 27BPBPB4090Q1ZM



ISO 9001:2015 Certified