

23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai - 400 701, INDIA. Phone: +91 93244 69890 Email: lab@gvmtesthouse.com www.gvmtesthouse.com



TESTING TRAINING

AUDITING

Test Order Ref: GVM/COATING/04673-3-1/01/2024 Date of Receipt:17.01.2024

Date: 07.02.2024 Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village - Vasind, Taluka - Shahapur, Vasind, Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample	: •,	Sample Supplied by the Customer
No. of Product tested	:	01 (One Only)
Customer's Reference	:	PO No. VSND/2010014020/SER/R/2620008355, dt11.01.2024
Condition of Sample	:	Satisfactory
Lab Reference Number	:	2024/JAN/04673-3-1
Sample Identification #	:	Dulux Velvet Touch Pearl Glo
Period of Test	:	19.01.2024 to 07.02.2024
Test Method #	:	ASTM D 4828-1994

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	7
3	Теа	100	5
4	Coffee	100	5
5	Highlighter	100	7
6	Crayon	100	10
7	Tomato Ketchup	100	10
8	Lipstick	100	7
9	Mud	100	10
10	Turmeric	100	7

Rating Scala as per ASTM D 4828

- 0 No change from original intensity (depth) of stain
- Slight change from original, but readily visible 3
- 5 Moderate change from original, slightly visible, and
- Large change from original, barely visible 7
- 10 All Stain removed

As furnished by the customer.

- Note: 1. The results relate only to the items tested.
 - 2. Report shall not be reproduced except in full, without the written approval of lab.
 - 3. Any correction invalidates this report.





23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai - 400 701, INDIA. Phone: +91 93244 69890 Email: lab@gvmtesthouse.com www.gvmtesthouse.com



TESTING TRAINING A

AUDITING

Test Order Ref: GVM/COATING/04673-3-2/01/2024 Date of Receipt:17.01.2024

Date: 07.02.2024 Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village – Vasind, Taluka – Shahapur, Vasind, Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample		Sample Supplied by the Customer	
No. of Product tested	:	01 (One Only)	
Customer's Reference	: *	PO No. VSND/2010014020/SER/R/2620008355, dt11.01.2024	
Condition of Sample	:	Satisfactory	
Lab Reference Number	:	2024/JAN/04673-3-1	
Sample Identification #	:	Dulux Velvet Touch Diamond Glo	
Period of Test	:	19.01.2024 to 07.02.2024	
Test Method #	:	ASTM D 4828-1994	

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	7
3	Теа	100	5
4	Coffee	100	5
5	Highlighter	100	7
6	Crayon	100	10
7	Tomato Ketchup	100	10
8	Lipstick	100	7
9	Mud	100	10
10	Turmeric	100	7

Rating Scala as per ASTM D 4828

- 1 No change from original intensity (depth) of stain
- 4 Slight change from original, but readily visible
 - 6 Moderate change from original, slightly visible, and
 - 7 Large change from original, barely visible
 - 10 All Stain removed

As furnished by the customer.

- Note: 1. The results relate only to the items tested.
 - 2. Report shall not be reproduced except in full, without the written approval of lab.
 - 3. Any correction invalidates this report.





23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node. Navi Mumbai - 400 701. INDIA. Phone: +91 93244 69890 Email: lab@gvmtesthouse.com www.gvmtesthouse.com



Date: 07.02.2024

Page No. 1 of 1

TESTING TRAINING AUDITING

Test Order Ref: GVM/COATING/04673-3-3/01/2024 Date of Receipt:17.01.2024

JSW PAINTS PRIVATE LIMITED

Vasind Village - Vasind, Taluka - Shahapur, Vasind, Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample		:	Sample Supplied by the Customer
No. of Product tested	1	:	01 (One Only)
Customer's Reference		:	PO No. VSND/2010014020/SER/R/2620008355, dt11.01.2024
Condition of Sample		:	Satisfactory
Lab Reference Number		:	2024/JAN/04673-3-3
Sample Identification #		:	Nerolac Impressions HD Premium Luxury Emulsion
Period of Test		:	19.01.2024 to 07.02.2024
Test Method #		:	ASTM D 4828-1994

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	10
3	Теа	100	7
4	Coffee	100	7
5	Highlighter	100	10
6	Crayon	100	10
7	Tomato Ketchup	100	7
8	Lipstick	100	5
9	Mud	100	10
10	Turmeric	100	5

Rating Scala as per ASTM D 4828

- 2 No change from original intensity (depth) of stain
- 5 Slight change from original, but readily visible
- 7 Moderate change from original, slightly visible, and
- 7 Large change from original, barely visible
- 10 All Stain removed

As furnished by the customer.

1. The results relate only to the items tested. Note:

- 2. Report shall not be reproduced except in full, without the written approval of lab.
- 3. Any correction invalidates this report.





23-24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node. Navi Mumbai - 400 701, INDIA. Phone: +91 93244 69890 Email: lab@gvmtesthouse.com www.gvmtesthouse.com



TESTING TRAINING AUDITING

Test Order Ref: GVM/COATING/04673-3-4/01/2024 Date of Receipt:17.01.2024

Date: 07.02.2024 Page No. 1 of 1

JSW PAINTS PRIVATE LIMITED

Vasind Village - Vasind, Taluka - Shahapur, Vasind, Thane, Maharashtra -421604

TEST REPORT ON STAIN RESISTANCE

Source of Sample	. :	Sample Supplied by the Customer	
No. of Product tested	:	01 (One Only)	
Customer's Reference	:	PO No. VSND/2010014020/SER/R/2620008355, dt11.01.2024	
Condition of Sample	:	Satisfactory	
Lab Reference Number	:	2024/JAN/04673-3-4	
Sample Identification #	• :	Nerolac Impressions Kashmir Luxury Emulsion	
Period of Test	:	19.01.2024 to 07.02.2024	
Test Method #	:	ASTM D 4828-1994	

TEST RESULTS:

S. N.	Stain Name #	Nos. of Wash Cycles	Evaluation of the condition of Stain after wash cycles
1	Pencil	100	10
2	Shoes Polish	100	10
3	Теа	100	7
4	Coffee	100	7
5	Highlighter	100	10
6	Crayon	100	10
7	Tomato Ketchup	100	7
8	Lipstick	100	7
9	Mud	100	10
10	Turmeric	100	7

Rating Scala as per ASTM D 4828

- 3 No change from original intensity (depth) of stain
- 6 Slight change from original, but readily visible
- Moderate change from original, slightly visible, and 8
- 7 Large change from original, barely visible
- 10 All Stain removed

As furnished by the customer.

1. The results relate only to the items tested. Note:

- 2. Report shall not be reproduced except in full, without the written approval of lab.
- 3. Any correction invalidates this report.

